WOVEN POLYPROPYLENE MEDIA

BLACK PEAK & VALLEY

Mechanical Properties	Test Method	Unit	Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632-91	lbs	255	225
Trapezoid Tear Strength	ASTM D 4533-91	lbs	120	110
Puncture Strength	ASTM D 4833-00	lbs	100	
Thickness	ASTM D 5199-01	mils	70	
Burst	ASTM D 3786-87	psi	450	
Air Flow	ASTM D 737-96	cfm	> 1500	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261-92	oz/yd^2	5.0
Fiber Content			100% PP

Filtration Manufacturing, Inc.
47 J. Faris Drive
Andalusia, AL 36421
Phone: (800) 239-9495
Fax: (800) 239-9798